
14 oz Aramid Non Woven with Membrane RZ™ Expanded PTFE

Product Specifications

FFI MATERIAL I.D.
382-STPS-84

US Units

Fiber Composition	Aramid
Industry Basis Weight, (oz/yd ²) (ASTM D-461-93)	13-15 oz /sq yd
Thickness, inches	.06-.09 in
Width, Inches	83"
Average Air Permeability (SCFM/ft ² @ 0.5" wg)	5-12 ft ³ /ft ² min
Continuous Service Temp., F°	400°
Mullen Burst Strength, psi	Min 420
Stability	max 2% residual shrink; max 2% residual stretch

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

Call for more info
(800) 367-1953



Visit us online
www.dustcollector-bags.com