



(800) 367-1953
TRUSTED MANUFACTURING

16 Ounce Polyester Non Woven Product Specifications FFI I.D. CODE 783-PS-84

US Units

Fiber Composition		Polyester	
Industry Basis Weight, (oz/yd² (ASTM D-461-93)	·)	15-17	
Thickness, inches		.0609	
Width, Inches		84	
Average Air Permeability (SCFM/ft² @ 0.5" wg)		25-45	
Continuous Service Temp., F°		275°	
Mullen Burst Strength, psi		400	
Stability	max 2% residual shrink; max 2% residual stretch		
Finish M) or	Glazed 1 side (16OZ-84-		
	Singed	Singed (16OZ-84-S)	

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

Call for more info

Visit us online

(800) 367-1953

www.dustcollector-bags.com